

Holes in a Quantum Spin Liquid

Guangyong Xu¹, G. Aeppli², M. E. Bisher², C. Broholm^{1,3}, J. F. DiTusa⁴, C. D. Frost⁵, T. Ito⁶, K. Oka⁶,
R. L. Paul³, H. Takagi⁷, and M. M. J. Treacy²

¹*Department of Physics and Astronomy, Johns Hopkins University, Baltimore, Maryland 21218, USA*

²*NEC Research Institute, 4 Independence Way, Princeton, New Jersey 08540, USA*

³*NIST Center for Neutron Research, Gaithersburg, Maryland 20899, USA*

⁴*Department of Physics and Astronomy, Louisiana State University, Baton Rouge, Louisiana 70803, USA*

⁵*ISIS Facility, Rutherford Appleton Laboratory, Chilton, Didcot, Oxon OX11 0QX, UK*

⁶*Electrotechnical Laboratory, Tsukuba 305, Japan*

⁷*Department of Advanced Materials Science, Graduate School of Frontier Sciences, University of Tokyo Hongo, Tokyo 113-8656, Japan*

Magnetic neutron scattering provides evidence for nucleation of antiferromagnetic droplets around impurities in a doped nickel-oxide based quantum magnet. The undoped parent compound contains a spin liquid with a cooperative singlet ground state and a gap in the magnetic excitation spectrum. Calcium doping creates excitations below the gap with an incommensurate structure factor. We show that weakly interacting antiferromagnetic droplets with a central phase shift of π and a size controlled by the correlation length of the quantum liquid can account for the data. The experiment provides a first quantitative impression of the magnetic polarization cloud associated with holes in a doped transition metal oxide.

Spin density modulations in transition metal oxides are receiving huge attention because of possible connections to high temperature superconductivity. The modulations appear upon introduction of charge carriers, via chemical substitution, into an insulating and antiferromagnetic parent compound, and tend to be static when the carriers are frozen, dynamic when they are mobile. Evidence for such modulations has been largely confined to materials whose magnetism and charge transport are quasi-two-dimensional(1-4), and whose parent insulators are ordered antiferromagnets. We provide evidence for analogous phenomena in a quasi-one-dimensional oxide(5), $\text{Y}_{2-x}\text{Ca}_x\text{BaNiO}_5$, for which the parent is a spin liquid by virtue of quantum fluctuations(6-10), and which has motivated considerable theoretical activity(11-16).

The key features of this orthorhombic material are the chains of NiO_6 octahedra (Fig. 1A). The octahedra are corner-sharing, which results in the dominance of magnetism(8) and electrical conduction (5) by the very simple ..O-Ni-O-Ni-O.. back-bone. The magnetic degree of freedom at each Ni site is the spin $S=1$ associated with the $3d^8$ configuration of Ni^{2+} . Each of the $S=1$ ions is coupled to its neighbors via antiferromagnetic (AFM) super-exchange through shared O^{2-} ions. Replacing the off-chain Y^{3+} by Ca^{2+} introduces holes primarily onto apical oxygen atoms in the chains and while the materials remain insulators, doping significantly increases conductivity at finite temperatures. Thus, $\text{Y}_{2-x}\text{Ca}_x\text{BaNiO}_5$ is a one-dimensional analog of the cuprates, where off- CuO_2 -plane chemical impurities donate holes to the CuO_2 planes.

Magnetic one-dimensionality causes the parent compound Y_2BaNiO_5 to be a spin liquid prevented from ordering antiferromagnetically by quantum fluctuations. The material is not an ordinary paramagnet with heavily damped spin fluctuations, but rather the magnetic analog of super-fluid ^4He because it has a macroscopically coherent quantum ground state and lacks static order. Affleck, Kennedy, Lieb and Tasaki (AKLT) provided a prescription for this state(17,18). They considered each $S=1$ degree of freedom as the triplet ground state formed between two ferromagnetically coupled $S=1/2$ degrees of freedom, in accord with atomic physics which posits a large and positive Hund's rule coupling between the two $S=1/2$ holes of Ni^{2+} . To understand the qualitative features of the ground and excited states of the spin-1 chain, they started from the limit of vanishing intra-atomic interactions between spin-1/2 holes. Because each site of the spin chain has as many nearest neighbors as $S=1/2$ degrees of freedom, there exists a macroscopic singlet with the full symmetry of the Hamiltonian wherein all $S=1/2$ degrees of freedom take part in nearest neighbor bond singlets (Fig 2A). Excitations from this "Valence Bond Solid" (VBS) state are triplets formed by broken valence bonds that propagate along the chain. The triplet band is separated from the VBS by an energy of order J corresponding to the energy required to create a triplet at rest. As the Ferromagnetic (FM) Hund's rule coupling is taken to much larger values than J these low energy states evolve adiabatically into the ground and excited states respectively of the $S=1$ chain. The major change is that for energies below the intra-atomic exchange energy, spin-1/2 degrees of freedom can be observed only as edge states, not in the bulk.

The triplet band can be observed experimentally for Y_2BaNiO_5 (Fig. 2A). An image of the magnetic neutron scattering intensity as a function of wave vector transfer $\vec{q}$ along the spin chains (in units of the inverse lattice spacing) and energy transfer, $\hbar\omega$, was obtained using time-of-flight neutron spectroscopy at the ISIS facility in the UK. Magnetic neutron scattering occurs only when $\hbar\omega$ and $\vec{q}$ lie on a dispersion relation, thus providing evidence for coherent triplet propagation along spin chains. What distinguishes this excitation from a spin wave is that it propagates in a medium with no static magnetic order. Key features are (i) a 9 meV Haldane gap(19), which corresponds to the

threshold energy for triplet creation, (ii) the magnetic excitation bandwidth of 62 meV that translates into an AFM exchange constant $J = 21$ meV, and (iii) vanishing intensity for $\tilde{q} = n2\pi$, which is evidence for a singlet ground state.

What happens when by Ca doping we add carriers to the quantum spin liquid of Fig. 2A?. Our $x = 0.095(5)$ sample (Fig. 2B) reveals excitations following a similar dispersion relation as for pure Y_2BaNiO_5 . However, near the former minimum at $\tilde{q} = \pi$, their intensity is substantially reduced and new magnetic scattering appears below the Haldane gap. More detailed data collected near and below the gap (Fig. 3B) show that near the gap energy, the scattering is clearly peaked at $\tilde{q} = \pi$ but for $\hbar\omega = 3 - 7$ meV it is most intense along two vertical lines, displaced symmetrically about π . Higher statistics energy-integrated $\tilde{q}$ -scans are shown (Fig. 4) that accurately quantify the incommensurate peaks for three single crystals with different levels of doping. Surprisingly, increased doping does not yield a proportional increase in the shift of the peaks from π . Specifically, if we fit the three data sets by the sum of two identical Lorentzians centered at $\pi \pm \delta\tilde{q}$ with half-widths-at-half-maximum, $\tilde{\kappa}$, we find that $\delta\tilde{q}$ extrapolates to a finite value in the dilute limit increasing with x as $\delta\tilde{q}(x)/\pi \approx 0.059(2) + 0.25(3)x$ (see inset to Fig. 4(B)). A similar x -dependence is found for $\tilde{\kappa}(x)/\pi \approx 0.047(3) + 0.20(6)x$ with the implication that a single length scale, which is finite in the limit $x \rightarrow 0$, controls both $\tilde{q}(x)$ and $\tilde{\kappa}(x)$.

There are various models which could produce the incommensurate fluctuations we have discovered in $\text{Y}_{2-x}\text{Ca}_x\text{BaNiO}_5$. The first proceeds from a charge-ordering hypothesis where the holes order periodically to minimize Coulomb repulsion and the spin system acquires a period commensurate with that of the hole lattice. The magnetic fluctuations are spin waves broadened in $\tilde{q}$ due to disorder in the hole lattice. Such a scenario is commonly supposed for the two-dimensional analog, doped La_2NiO_4 , where key experimental support came from electron(20) and neutron diffraction(21,22). Thus inspired, we used both techniques to search for hole ordering in $\text{Y}_{2-x}\text{Ca}_x\text{BaNiO}_5$ down to 15K. The failure of the search makes the charge ordering explanation of our experiments unlikely. Furthermore, in the simplest picture, the hole density has the same period as the spin density squared so that $\delta\tilde{q}(x)/\pi \approx x$, which is entirely inconsistent with Fig. 4 (dashed line in the inset).

A second possibility is to identify the incommensurate magnetic fluctuations with electron-hole pair excitations from the one-dimensional hole liquid associated with mobile $S=1/2$ hole propagation through the VBS(11). The wave-vectors $\pi \pm \delta\tilde{q}$ would be vectors spanning the Fermi surface while the vertical nature of the incommensurate streaks (Fig. 3) would imply a Fermi velocity exceeding 0.5 eV·Ångstrom. The problem with this picture is that even if we can ignore that the samples seem not to be proper metals - the resistivities(5) are high at low T - the Fermi sea is expected to grow in proportion to x leading to $\delta\tilde{q}(x) \approx x$, a result again contradicted by Fig. 4.

A last possibility starts from consideration(13) of the magnetic structure factor for a single static hole donated to the NiO chain by the Ca ions. Because it carries a spin, a hole on a super-exchange mediating oxygen atom induces an effective ferromagnetic Ni-Ni interaction(23,24). The hole-carrying oxygen divides the chain into two semi-infinite segments, for which wave-functions can be constructed from a basis set which is the direct product of wave-functions for each segment and for the hole on the intervening oxygen. The ground state wave-function for a semi-infinite segment is a doublet rather than the singlet wave-function for the unterminated chain. Pictorially, (Fig. 1B-C) the chain ends have unpaired spins because only one of the two AKLT spins, which together represent the $S=1$ sites, can be paired with an AKLT spin on a neighboring site. The effective ferromagnetic interaction between semi-infinite chains yields a ground state with inversion symmetry about the oxygen site. The edge states are not localized on Ni^{2+} atoms neighboring the hole, but extend into the chain with AFM modulation over a distance of order the Haldane spin correlation length, κ^{-1} . As a result, ground state correlations $\langle S_0 S_j \rangle$ between spins at site 0 and site j , where the FM bond occurs between sites -1 and 0 , should take the form $(-1)^j e^{-|j|\kappa}$ for $j \geq 0$ and $(-1)^{j+1} e^{-|j+1|\kappa}$ for $j \leq -1$.

Neutron scattering measures the modulus squared Fourier transform of the spin polarization. For the ground state associated with a single FM bond inserted within an infinite chain, this is

$$S(\tilde{q}) = \left| \frac{(1 + e^\kappa) \cos(\tilde{q}/2)}{\cosh \kappa + \cos \tilde{q}} \right|^2. \quad (1)$$

Eq. 1 describes a function with nodes for $\tilde{q} = (2n + 1)\pi$ and pairs of peaks, with half widths and incommensurability of order κ (see dashed line in Fig. 4A). Thus, the description leading to Eq. 1 does have a chance of accounting for a key feature of our data. There are however three difficulties, the first being that the nodes predicted by Eq. 1 are not seen experimentally. The second problem is that we have neglected the spin on the intervening oxygen. The third is that Eq. 1 describes the ground state for a single FM bond, implying that neutron scattering should be elastic, not inelastic as seen experimentally.

The first difficulty has a simple resolution. At finite hole densities the polarization clouds overlap and the isolated impurity model is inadequate. A crude model, which considers the overlaps, simply truncates the polarization clouds at neighboring impurity sites. Because FM impurity bonds are randomly distributed, the inversion symmetry characterizing isolated impurities is broken thus allowing intensity at $\tilde{q} = \pi$. Because we know the impurity density, x ,

from neutron activation analysis, the only parameters in such a description are the extent of the polarization cloud, κ^{-1} , which we adjusted to optimize the fit to our data. As shown by the red lines in Fig. 4 the model provides a good account of the data with $\kappa^{-1} = 8.1(2), 7.3(2)$, and $7.2(5)$ for $x = 0.04, 0.095$, and 0.14 respectively. These values are close to the exponential decay length of 6.03 calculated for the AFM spin polarization at the end of an $S=1$ chain(25).

The modeling described so far does not include the spins of the holes responsible for the effective FM couplings between Ni^{2+} ions. The holes reside in oxygen orbitals of $\text{Y}_{2-x}\text{Ca}_x\text{BaNiO}_5$ (5), but are almost certainly not confined to single, isolated oxygens. We have consequently generalized Eq. 1 to take into account the hole spins, with - for the sake of definiteness - the same net amplitude as either of the Ni^{2+} spins next to the FM bond, and distributed (with exponential decay) over ℓ lattice sites centered on the FM bond. As long as ℓ exceeds the modest value of 2, comparable to the localization length deduced from transport data (5), the pronounced asymmetry about π which occurs when $\ell = 0$ is relieved sufficiently to produce fits indistinguishable from those in Fig. 4.

How do we account for the inelasticity of the incommensurate signal? One approach is to view the chain as consisting not of the original $S=1$ degrees of freedom but of the composite spin degrees of freedom induced around holes. The latter interact via overlapping AFM polarization clouds and hole wave functions, to produce effective couplings of random sign because the impurity spacing can be even or odd multiples of the Ni-Ni separation. With weak interchain coupling the ground state is likely to be a spin glass, as deduced from other experiments(26) on $\text{Y}_{2-x}\text{Ca}_x\text{BaNiO}_5$. The “incommensurate” nature of the excitations continues to follow from the structure factor of the spin part of the hole wavefunctions.

In summary, we have measured the magnetic fluctuations in single crystals of a doped one-dimensional spin liquid. At energies above the spin gap, the triplet excitations of the parent compound, Y_2BaNiO_5 , persist with doping. However, below the gap, we find new excitations with a broad spectrum and characteristic wave vectors that are displaced from the zone boundary by an amount of order the inverse correlation-length for the parent. The incommensurate fluctuations, encountered here in a doped one-dimensional transition metal oxide, resemble those seen in metallic cuprates. However, one-dimensionality makes them easier to model for Y_2BaNiO_5 , and our analysis reveals that “incommensurate” peaks arise naturally even without hole order because of the characteristic spin density modulation that develops around a defect in the singlet ground state of a quantum spin liquid. This phenomenon accounts for the weak dependence of the incommensurability on doping in the one-dimensional nickelate. Indeed, $\text{Y}_{2-x}\text{Ca}_x\text{BaNiO}_5$ gives us our first quantitative impression of the magnetic polarization cloud associated with the holes in a doped transition metal oxide. Our results imply that the spin part of the hole wave-function is actually the edge state nucleated by the hole in a quantum spin fluid.

References

1. S.-W. Cheong et al., *Phys. Rev. Lett.* **67**, 1791 (1991).
2. S. M. Hayden et al., *Phys. Rev. Lett.* **68**, 1061 (1992).
3. H. A. Mook et al., *Nature* **395**, 580 (1998).
4. J. M. Tranquada, B. J. Sternlieb, J. D. Axe, Y. Nakamura, S. Uchida, *Nature* **375**, 561 (1995).
5. J. F. DiTusa et al., *Phys. Rev. Lett.* **73**, 1857 (1994).
6. J. Darriet and L.P. Regnault, *Solid State Commun.* **86**, 409 (1993).
7. J. F. DiTusa et al., *Physica B* **194-196**, 181 (1994).
8. G. Xu, et al., *Phys. Rev. B* **54**, R6827 (1996).
9. T. Sakaguchi, K. Kakurai, T. Yokoo, J. Akimitsu, *Phys. Soc. Japan* **65**, 3025 (1996).
10. A. Keren et al., *Phys. Rev. Lett.* **74**, 3471 (1995).
11. E. Dagotto, J. Riera, A. Sandvik, A. Moreo, *Phys. Rev. Lett.* **76**, 1731 (1996).
12. Z.-Y. Lu, Z.-B. Su, L. Yu, *Phys. Rev. Lett.* **74**, 4297 (1995).
13. K. Penc and H. Shiba, *Phys. Rev. B* **52**, R715 (1995).
14. S. Fujimoto and N. Kawakami, *Phys. Rev. B* **52**, 6189 (1995).
15. E. S. Sorensen and I. Affleck, *Phys. Rev. B* **51**, 16115 (1995).
16. R. A. Hyman, K. Yang, R. N. Bhatt, S. M. Girvin, *Phys. Rev. Lett.* **76**, 839 (1996).
17. I. Affleck, T. Kennedy, E. H. Lieb, H. Tasaki, *Phys. Rev. Lett.* **59**, 799 (1987).
18. T. Kennedy, *J. Phys. Cond. Matter* **2**, 5737 (1990).
19. F. D. M. Haldane, *Phys. Lett.* **93A**, 464 (1983).
20. C. H. Chen, S.-W. Cheong, A. S. Cooper, *Phys. Rev. Lett.* **71**, 2461 (1993).
21. J. M. Tranquada, D. J. Buttrey, V. Sachan, J. E. Lorenzo, *Phys. Rev. Lett.* **73**, 1003 (1994).
22. S.-H. Lee and S.-W. Cheong, *Phys. Rev. Lett.* **79**, 2514 (1997).
23. V.J.Emery and G. Reiter, *Phys. Rev. B* **38**, 4547(1988).
24. A. Aharony et al., *Phys. Rev. Lett.* **60**, 1330(1988).
25. S. R. White and D. A. Huse, *Phys. Rev. B* **48**, 3844 (1993).
26. K. Kojima, et al., *Phys. Rev. Lett.* **74**, 3471 (1995).
27. We thank T. M. Rice, A. J. Millis, and Q. Huang for useful discussions and A. Krishnan for TEM measurements. Work at JHU was supported by the NSF under DMR-9453362. Work at LSU was supported by the NSF under DMR-9702690 and the State of Louisiana Board of Regents under LEQSF(RF/1996-99)-RD-A-05. This work utilized neutron research facilities supported by NIST and the NSF through DMR-9423101.

FIG. 1. (A) Chain unit of Y_2BaNiO_5 featuring nickel atoms with octahedral oxygen coordination and Ca^{2+} impurities on Y^{3+} sites. (B) Schematic of $S=1/2$ degrees of freedom at the edges of the AKLT state. (C) Ferromagnetically coupled chain-end $S=1/2$ degrees of freedom.

FIG. 2. Overview of magnetic fluctuations in (A) pure and (B) 9.5% doped Y_2BaNiO_5 at $T=10\text{K}$. The initial neutron beam energy was 90 meV and the chain axis was perpendicular to the incident beam direction. Boxes indicate regions examined in Fig. 3. The color bar shows values for $\frac{ki}{kf} \frac{d^2\sigma}{d\Omega dE_f}$ in units of mbarn meV^{-1} per Ni.

FIG. 3. Low energy detail of magnetic excitations in (A) pure and (B) 9.5% doped Y_2BaNiO_5 . (A) shows time-of-flight data at $T=10\text{K}$ (MARI spectrometer, ISIS pulsed neutron source) while (B) shows data collected at $T=1.5\text{K}$ using triple-axis spectrometers (SPINS and BT2 at NIST steady state nuclear reactor with final energies 5 meV and 14.7 meV respectively). The color bar shows values for $\frac{ki}{kf} \frac{d^2\sigma}{d\Omega dE_f}$ in units of mbarn meV^{-1} per Ni.

FIG. 4. $\tilde{q}$ -scans, collected using SPINS at NIST, through the incommensurate peaks at fixed energy transfer of 4.5 meV for three different hole concentrations. The energy resolution of the spectrometer was 2 meV FWHM. The dashed green line in A shows the single impurity model Eq. 1 convolved with the instrumental resolution (solid bar). The red lines take into account that neighboring impurities truncate the spin polarization cloud around an impurity bond. Inset in B shows half the distance $\delta\tilde{q}(x)/\pi$ between the peaks of two Lorentzians superposed to fit the data.

This figure "figure1.jpg" is available in "jpg" format from:

<http://arXiv.org/ps/cond-mat/0102445v2>

This figure "figure2.jpg" is available in "jpg" format from:

<http://arXiv.org/ps/cond-mat/0102445v2>

This figure "figure3.jpg" is available in "jpg" format from:

<http://arXiv.org/ps/cond-mat/0102445v2>

This figure "figure4.jpg" is available in "jpg" format from:

<http://arXiv.org/ps/cond-mat/0102445v2>